



PRODUCT PROFILE

068 EXTERIOR PRIMER

100% ACRYLIC

1950 Dr. Martin Luther King Jr. Pkwy. - Chico, Ca 95928 - (530) 345-9595 - Fax (530) 345-3589

DESCRIPTION:

068 exterior primer is a fast drying 100% acrylic primer for wood and masonry surfaces. 068 is resistant to tannin bleed found in certain woods such as redwood and cedar. Recommended for use as a primer or base coat for all exterior oil and water base finishes.

PHYSICAL PROPERTIES	
COLOR	WHITE
FINISH	FLAT
SOLVENT	WATER
DRY TO TOUCH	1-2 HOURS
% SOLIDS BY VOLUME	35%
% SOLIDS BY WEIGHT	47%
COVERAGE	250-400 SQUARE FEET
VISCOSITY	90-95 KREB UNITS
RECOAT TIME	4 HOURS WATER BASE 24 HOURS OIL BASE

V.O.C.: LESS THAN 100 GRAMS PER LITER

ADVANTAGES:

- * Excellent stain blockage
- * Extremely durable
- * Meets clean air standards
- * Outstanding adhesion
- * Water thinned
- * Fast Drying
- * Easy application
- * Excellent base coat

**Refer to label for cautions and warnings



PRODUCT PROFILE

068 EXTERIOR PRIMER

100% ACRYLIC

1950 Dr. Martin Luther King Jr. Pkwy. - Chico, Ca 95928 - (530) 345-9595 - Fax (530) 345-3589

TYPE OF PRODUCT:

A water base exterior 100% acrylic primer for wood and masonry surfaces. Excellent stain blocking characteristics. Recommended as a primer for oil or water base finishes.

TYPICAL USES:

068 primer was designed particularly for use on staining types of wood like redwood and cedar to prevent tannin bleed. Also, as a base coat for all exterior finishes.

SURFACE PREPARATION:

Be sure all surfaces are dry, free from dirt, grease, wax, chalky paint, rust, efflorescence and stains. Dull or etch glossy, glazed or dense surfaces. Neutralize alkali conditions, remove and kill all mildew or any other contamination that would adversely affect the performance of this coating.

APPLICATION:

May be applied by brush, roller or airless spray equipment. Do not apply in temperature below 50°F.

DRYING TIME:

1-2 hours. For proper penetration and adhesion, allow 4-6 hours before application of water base finish coat. Allow 24 hours if priming wood with tannins, i.e. cedar and redwood or top coating with oil base. Damp and cool weather could extend drying time.

NEW SURFACES:

Apply one uniform coat to seal redwood, fir, masonry, etc. A second coat may be needed in areas where staining is severe.

PREVIOUSLY PAINTED SURFACES:

Use 068 as a spot primer over bare wood, patched areas or prime entire area before repainting.

COVERAGE:

200-400 square feet per gallon, depending on porosity of the surface.

THINNING AND CLEAN-UP:

Formulated ready for use. If thinning is necessary use small amount of water. Do not over thin. Clean brushes and equipment with water immediately after use.

COLORS:

White

PACKAGE SIZES: 5 gallon, 1 gallon, quarts

APPROX. WEIGHT PER GAL: 11.1 LB.