



**PRODUCT PROFILE**  
**850 EXTERIOR LOW SHEEN LATEX**  
**100% ACRYLIC**

1950 Dr. Martin Luther King Jr. Pkwy. - Chico, Ca 95928 - (530) 345-9595 - Fax (530) 345-3589

**DESCRIPTION:**

850 Exterior low sheen latex is a fast drying 100% acrylic paint for new or old wood and masonry surfaces. 850 is very resistant to soiling, fading and chalking under extreme weather conditions.

<b>PHYSICAL PROPERTIES</b>	
COLOR	WHITE AND BASES
FINISH	LOW SHEEN
SOLVENT	WATER
DRY TO TOUCH	1-3 HOURS
% SOLIDS BY VOLUME	37%
% SOLIDS BY WEIGHT	47%
COVERAGE	300-400 SQUARE FEET
VISCOSITY	90-95 KREB UNITS
RECOAT TIME	4-6 HOURS

**V.O.C.: LESS THAN 150 GRAMS PER LITER**

**ADVANTAGES:**

- \* Fast drying
- \* Superior color retention
- \* Meets clean air standards
- \* Flexible strength
- \* Water thinned
- \* Extremely durable
- \* Easy application
- \* Outstanding adhesion

\*\*Refer to label for cautions and warnings



## **PRODUCT PROFILE**

### **850 EXTERIOR LOW SHEEN LATEX**

### **100% ACRYLIC**

1950 Dr. Martin Luther King Jr. Pkwy. - Chico, Ca 95928 - (530) 345-9595 - Fax (530) 345-3589

#### **TYPE OF PRODUCT:**

A fast drying acrylic low sheen finish for all kinds of exterior surfaces. Very resistant to soiling, fading and chalking under extreme weather conditions.

#### **TYPICAL USES:**

All exterior surfaces where durability and washability are desired. Excellent for repainting wood, stucco, or aluminum siding that has weathered and faded.

#### **SURFACE PREPARATION:**

Be sure all surfaces are dry, free from dirt, grease, wax, chalky paint, rust, efflorescence and stains. Dull or etch glossy, glazed or dense surfaces. Neutralize alkali conditions, remove and kill all mildew or any other contamination that would adversely affect the performance of this coating.

#### **APPLICATION:**

May be applied by brush, roller or airless spray equipment. If brushing, a good quality nylon brush is recommended. Avoid applying in direct hot sunlight, paint in the shade if possible. Do not apply in temperature below 50°F.

#### **DRYING TIME:**

1-3 hours under normal conditions, recoat in 4-6 hours.

#### **PREVIOUSLY PAINTED SURFACES:**

Previously painted surfaces in good sound condition do not require priming. Prime bare wood and apply full coat of 850.

#### **NEW SURFACES:**

Prime with exterior primer either alkyd or latex type. Allow stucco, concrete, block, and brick a minimum of 60 days curing to reduce moisture and alkali before painting.

#### **COVERAGE:**

300-400 square feet per gallon over smooth sealed surfaces.

#### **THINNING AND CLEAN-UP:**

Formulated ready for use. If thinning is necessary use small amount of water. Do not over thin. Clean brushes and equipment with water immediately after use.

#### **COLORS:**

White and Tint Bases.

**PACKAGE SIZES:** 5 gallon, 1 gallon, quarts

**APPROX. WEIGHT PER GAL:** 10.6 LB.